



# Robertson Microlit Laboratories

1705 U.S. Highway 46 / Suite 1D / Ledgewood, NJ 07852 / (973) 966-6668 / Fax: (973) 966-0136  
www.robertson-microlit.com results@robertson-microlit.com

Naresh Patel  
ITW Pro Brands

Date: 7/10/17

Results of Analysis  
Sample Number:  
High Purity Red F.T. T301, Test #764

Element	Results (ppm)	Requirements
<i>Total Halogens:</i>	....	250 Maximum
Bromine	<1ppm	100 Maximum
Chlorine	<1ppm	100 Maximum
Fluorine	<1ppm	100 Maximum
Iodine	<6ppm	100 Maximum
Lead	<1ppm	25 Maximum
Sulfur	83ppm	250 Maximum
<i>Low Melting Point Elements:</i>	....	300 Maximum
Antimony	1ppm	100 Maximum
Bismuth	5ppm	100 Maximum
Boron	35ppm	100 Maximum
Cadmium	<1ppm	100 Maximum
Copper	4ppm	100 Maximum
Mercury	<1ppm	100 Maximum
Phosphorus	1%	100 Maximum
Selenium	10ppm	100 Maximum
Silver	9ppm	100 Maximum
Sodium	174ppm	100 Maximum
Tellurium	<1ppm	100 Maximum
Thallium	<1ppm	100 Maximum
Tin	<1ppm	100 Maximum
Zinc	2ppm	100 Maximum

Meets GE Specification #D50TF8 excluding Phosphorus and Sodium

QA:   
Dr. Robert Di Vincenzo