



Robertson Microlit Laboratories

1705 U.S. Highway 46 / Suite 1D / Ledgewood, NJ 07852 / (973) 966-6668 / Fax: (973) 966-0136
www.robertson-microlit.com results@robertson-microlit.com

Naresh Patel
ITW Pro Brands

Date: 7/10/17

Results of Analysis
Sample Number:
Z916 High Purity Yellow, Test #763

Analysis	Results (ppm)	Requirements (ppm)
<i>Total Halogens</i>	250 maximum
Bromine	<1ppm	100 maximum
Chlorine	69ppm	100 maximum
Fluorine	77ppm	100 maximum
Iodine	<7ppm	100 maximum
Lead	<1ppm	25 maximum
Sulfur	188ppm	250 maximum
<i>Low Melting Point Elements</i>	300 maximum
Antimony	99ppm	100 maximum
Bismuth	4ppm	100 maximum
Boron	27ppm	100 maximum
Cadmium	<1ppm	100 maximum
Copper	<1ppm	100 maximum
Mercury	<1ppm	100 maximum
Phosphorus	29%	100 maximum
Selenium	6ppm	100 maximum
Silver	4ppm	100 maximum
Sodium	582ppm	100 maximum
Tellurium	<1ppm	100 maximum
Thallium	<1ppm	100 maximum
Tin	22ppm	100 maximum
Zinc	8ppm	100 maximum

Meets GE Specifications #D50TF8 excluding Phosphorus and Sodium

QA:


Dr. Robert Di Vincenzo